

Crystalline Firing Schedule No. 1 (Basic):

Segment°F/HrTarget Temp.Hold (hr.min)

1	350	1000	00.00
2	750	1900	00.00
3	200	2000	00.00
4	108	2232	00.00
5	9999	1950	01.00

This Basic firing is a good all-round schedule that should fit most kilns and applications. The hold in the last segment can be increased or decreased and will affect crystal size.

Crystalline Firing Schedule No. 2 (Slow Cool)

Segment°F/HrTarget Temp.Hold (hr.min)

1	350	1000	00.00
2	750	1900	00.00
3	200	2000	00.00
4	108	2232	00.00
5	9999	2000	00.15
6	50	1900	00.00

This firing schedule adds an additional cooling segment which can produce more matte crystallization.